

Stratocell[®] S Anti Static

Closed cell Polyethylene foam, CFC and HCFC free.

<u>PROPERTIES</u>	<u>TEST METHOD</u>	<u>UNIT</u>	<u>VALUE</u>
DENSITY	DIN 53420	Kg/m ³	30
TENSILE STRENGTH	DIN 53571	N/mm ²	
Extrusion direction			0,318
Cross direction			0,227
ELONGATION AT BREAK	DIN 53571	%	
Extrusion direction			70
Cross direction			65
COMPRESSION STRENGTH	DIN 53577	N/mm ²	
25 % (4th compression)			0,031
50 % (4th compression)			0,091
70 % (4th compression)			0,221
THERMAL STABILITY (24h at 70° C)	ASTM D-3575-S	%	<3
THERMAL CONDUCTIVITY	ASTM C-177	W/mK	0,055
CELL SIZE	BS 4443/1 Met.4	Cells/25 mm	≥ 26
WATER ABSORPTION (after 24 hours)	DIN 53428	Vol %	0,7
SELF ESTINGUISHED (FR version)	UL 94 HF	Class	1
DECAY TIME From ±5 kV to ±50 V	Mil-B 81705 D Standard 101C Method 4046	Sec.	< 2
SURFACE RESISTIVITY	ASTM D-257	Ohms/Sq.	< 10 ¹³

The information provided in this data sheet is in good faith.
 No liability is, however, accepted for errors and omission and in no circumstances shall Sealed Air be liable in damages for loss or injury arising directly or as a consequence of the publication of this data sheet.